

Aluminium alloy L156 – 2014A T4 is a medium strength sheet and strip specification.

The standard specifying this grade has been superseded by BSEN 2395

Chemical Composition

Element	% Present
Si	0.5-0.9
Fe	0.5 Max
Cu	3.9-5.0
Mn	0.4-1.2
Cr	0.1 Max
Mg	0.2-0.8
Zn	0.25 Max
Ni	0.1 Max
Ti	0.15 Max
Ti & Zr	0.2 Max
Al	Balance

Alloy Designations

Aluminium alloy L156 has similarities to the following standard designations and specifications: 2014A

Physical Properties

Property	Value
Density	2.80 g/cm ³
Melting Point	640 °C
Modulus of Elasticity	73 GPa
Electrical Resistivity	40% IACS
Thermal Conductivity	155 W/m.K
Thermal Expansion	22.8 x10 ⁻⁶ /K

Mechanical Properties

Temper	Min
Proof Stress 0.2% (MPa)	255
Tensile Strength (MPa)	400
Shear Strength (MPa)	260 Typ
Elongation A5 (%)	14
Hardness Vickers (HV)	120 Typ

Typ = Typical

Temper

The most common tempers for L156 aluminium is:

- ◆ T4 – Solution heat treated and naturally or artificially aged
- ◆ As Rolled

Supplied Forms

L156 aluminium is supplied as Clad Sheet and Strip. ■

This Data is indicative only and must not be seen as a substitute for the full specification from which it is drawn.

In particular, the mechanical property requirements vary widely with temper, product and product dimensions.

The information is based on our present knowledge and is given in good faith. However, no liability will be accepted by the Company in respect of any action taken by any third party in reliance thereon

As the products detailed may be used for a wide variety of purposes and as the Company has no control over their use; the Company specifically excludes all conditions or warranties expressed or implied by statute or otherwise as to dimensions, properties and/or fitness for any particular purpose. Any advice given by the Company to any third party is given for that party's assistance only and without liability on the part of the Company.

Any contract between the Company and a customer will be subject to the Company's Conditions of Sale. The extent of the Company's liabilities to any customer is clearly set out in those Conditions; a copy of which is available on request.